

We claim:

1. An etching solution, consisting essentially of combining hydrofluoric acid and hydrogen peroxide in water.

5 2. The etching solution of claim 1 wherein said hydrofluoric acid has a concentration of 49%.

3. The etching solution of claim 1 wherein said hydrogen peroxide has a concentration of 29%-30%.

10

4. The etching solution of claim 1 wherein a volume ratio of hydrofluoric acid: hydrogen peroxide: water is 2:1:21.

5. The etching solution of claim 1 wherein said etching
15 solution is used at room temperature.

6. The etching solution of claim 1 wherein said etching solution is used at temperatures from 40°C to 50°C.

7. A solution for etching TaN during semiconductor device processing, consisting essentially of combining HF with a concentration of 49% with H_2O_2 with a concentration of 29%-30% in deionized water.

5

8. The solution of claim 7 wherein said solution has a volume ratio greater than 1:1:20 of HF: H_2O_2 :deionized water.

9. The solution of claim 7 wherein said solution has a
10 volume ratio of 2:1:21 of HF: H_2O_2 :deionized water.

10. The solution of claim 7 wherein said solution has a volume ratio of 3:2:10 of HF: H_2O_2 :deionized water.

11. The solution of claim 7 wherein said solution has a
15 volume ratio of 3:1:10 of HF: H_2O_2 :deionized water.

12. The solution of claim 7 wherein said solution is used at room temperature.

20

13. The solution of claim 7 wherein said solution is used at temperatures from 40°C to 50°C.

14. A solution for etching one or more of the following:
TaN, TiN, Cu, FSG, TEOS, and SiN in silicon device
processing, consisting essentially of combining HF with a
concentration of 49% with H₂O₂ with a concentration of 29%-
5 30% in deionized water at room temperature.

15. The solution of claim 14 wherein said solution has a
volume ratio of 2:1:21 of HF:H₂O₂:deionized water.

10 16. The solution of claim 14 wherein said solution has a
volume ratio of 3:2:10 of HF:H₂O₂:deionized water.

17. The solution of claim 14 wherein said solution has a
volume ratio of 3:1:10 of HF:H₂O₂:deionized water.

18. A solution for etching TaN, TiN, Cu, FSG, TEOS, and SiN
in silicon device processing, consisting essentially of
combining HF with a concentration of 49% with H₂O₂ with a
concentration of 29%-30% in deionized water from 40°C to
5 50°C.

19. The solution of claim 18 wherein said solution has a
volume ratio of 2:1:21 of HF:H₂O₂:deionized water.

10 20. The solution of claim 18 wherein said solution has a
volume ratio of 3:2:10 of HF:H₂O₂:deionized water.

21. The solution of claim 18 wherein said solution has a
volume ratio of 3:1:10 of HF:H₂O₂:deionized water.

15

22. A method for etching one or more of the following: TaN, TiN, Cu, FSG, TEOS, and SiN from a semiconductor body in semiconductor device processing, comprising:

5 forming a solution by combining HF with a concentration of 49% with H₂O₂ with a concentration of 29%-30% in deionized water; and

 applying said solution to said semiconductor body with
10 said solution being at room temperature.

23. The method of claim 22 wherein said forming a solution further comprises using a volume ratio greater than 1:1:20 of HF:H₂O₂:deionized water.

15

24. The method of claim 22 wherein said forming a solution further comprises using a volume ratio of 2:1:21 of HF:H₂O₂:deionized water.

20 25. The method of claim 22 wherein said method further comprises applying said solution in the presence of photoresist.

26. A method for etching one or more of the following: TaN, TiN, Cu, FSG, TEOS, and SiN from a semiconductor body in semiconductor device processing, comprising:

5 forming a solution by combining HF with a concentration of 49% with H₂O₂ with a concentration of 29%-30% in deionized water; and

 applying said solution to said semiconductor body with
10 said solution being at a temperature of 40°C to 50°C.

27. The method of claim 26 wherein said forming a solution further comprises using a volume ratio greater than 1:1:20 of HF:H₂O₂:deionized water.

15

28. The method of claim 26 wherein said forming a solution further comprises using a volume ratio of 2:1:21 of HF:H₂O₂:deionized water.

20 29. The method of claim 26 wherein said method further comprises applying said solution in the presence of photoresist.